

SOLAR BRONZE 35 XTRA EXTERNAL

Performance Data

Total Solar Energy Rejected	71%
Total Solar Energy Reflected	52%
Total Solar Energy Absorbed	27%
Total Solar Energy Transmitted	21%
Visible Light Transmitted	33%
Visible Light Reflected	28%
Ultra Violet Light Rejected	99.9%
Shading Coefficient	0.33
Solar Heat Gain Coeff. (g Value)	0.29
Winter U Value	1.04
Emissivity	0.84
Glare Reduction	64%

Performance Guide

Solar Heat Rejection	★ ★ ★ ★ ☆
Glare Reduction	★ ★ ★ ☆ ☆
UV Reduction	★ ★ ★ ★ ★
Fade Reduction	★ ★ ★ ★ ☆
Safety & Security	☆ ☆ ☆ ☆ ☆
One-Way Privacy	★ ★ ☆ ☆ ☆
Two-Way Privacy	☆ ☆ ☆ ☆ ☆
Scratch Coating	Yes
Warranty Period	4 Years Vertical 2.5 Years Sloping

Key: Excellent - ★★★★★ Some Benefit - ★★★☆☆ N/A - ☆☆☆☆☆

Film Notes

Externally applied sputtered medium bronze provides an attractive yet highly effective solution to heat and glare problems. Edge sealant required.

Please refer to front pages for explanations on performance data, performance guide and application restrictions.

