

TITAN 50 XTRA EXTERNAL

Performance Data

Total Solar Energy Rejected	49%
Total Solar Energy Reflected	22%
Total Solar Energy Absorbed	38%
Total Solar Energy Transmitted	40%
Visible Light Transmitted	52%
Visible Light Reflected	19%
Ultra Violet Light Rejected	99.9%
Shading Coefficient	0.59
Solar Heat Gain Coeff. (g Value)	0.51
Winter U Value	1.04
Emissivity	0.84
Glare Reduction	41%

Performance Guide

Solar Heat Rejection	★ ★ ★ ☆ ☆
Glare Reduction	★ ☆ ☆ ☆ ☆
UV Reduction	★ ★ ★ ★ ★
Fade Reduction	★ ★ ★ ☆ ☆
Safety & Security	☆ ☆ ☆ ☆ ☆
One-Way Privacy	☆ ☆ ☆ ☆ ☆
Two-Way Privacy	☆ ☆ ☆ ☆ ☆
Scratch Coating	Yes
Warranty Period	4 Years Vertical 2.5 Years Sloping

Key: Excellent - ★★★★★ Some Benefit - ★☆☆☆☆ N/A - ☆☆☆☆☆

Film Notes

Discreet neutral film with excellent heat and glare performance. Low internal reflectance. Ideal for listed buildings where internal grade prohibited. Edge sealant needed for warranty. Nano technology will not alter in colour.

Please refer to front pages for explanations on performance data, performance guide and application restrictions.

