

COOLKOTE SOLARLUX PAINT

Performance Data

Standard Colour	White
Dry appearance	Translucent matt
Spreading Rate	approx 12sq.mts undiluted
Touch dry @20°C	approx 40 mins
Recoating @20°C	approx 2 hours
Application methods	Foam roller
Substrates	Polycarbonate, glass, bitumen, plastics
Cleaning	Clean water
Solar performance	Reflects up to 85%
UV Reduction	90%
Glare Reduction	80%

Performance Guide

Solar Heat Rejection	★ ★ ★ ★ ★
Glare Reduction	★ ★ ★ ★ ★
UV Reduction	★ ★ ★ ★ ☆
Fade Reduction	★ ★ ★ ☆ ☆
Safety & Security	☆ ☆ ☆ ☆ ☆
One-Way Privacy	★ ★ ★ ★ ★
Two-Way Privacy	☆ ☆ ☆ ☆ ☆
Scratch Coating	☆ ☆ ☆ ☆ ☆
Life Expectancy	10 Years

Key: Excellent - ★★★★★ Some Benefit - ★☆☆☆☆ N/A - ☆☆☆☆☆

Film Notes

A durable water based flexible resin to provide a cost effective solution in industrial and commercial working environments. Ideal for reducing heat build up with easy application and long lifespan. See Technical and MSDS Datasheets for further details.

Please refer to your supplier for explanations on performance data, performance guide and application restriction

