

WHITEOUT

Performance Data

Total Solar Energy Rejected	70%
Solar Energy Reflected	40%
Solar Energy Absorbed	43%
Solar Energy Transmitted	17%
Visible Light Transmitted	13%
Visible Light Reflected	54%
Ultra Violet Light Rejected	95%
Shading Coefficient	0.35
Solar Heat Gain Coeff. (g Value)	-
Emissivity	0.86
Glare Reduction	86%

Performance Guide

Solar Heat Rejection	★ ★ ★ ★ ☆
Glare Reduction	★ ★ ★ ★ ★
UV Reduction	★ ★ ★ ★ ★
Fade Reduction	★ ★ ★ ★ ★
Safety & Security	☆ ☆ ☆ ☆ ☆
One-Way Privacy	☆ ☆ ☆ ☆ ☆
Two-Way Privacy	★ ★ ★ ★ ☆
Scratch Coating	Yes
Warranty Period	5 Years

Key: Excellent - ★★★★★ Some Benefit - ★☆☆☆☆ N/A - ☆☆☆☆☆

Film Notes

No vision and low absorption makes whiteout a good safe choice for most glazing types.

Please refer to your supplier for explanations on performance data, performance guide and application restrictions.

