

10 MIL OPTITUNE 30

Performance Data

Total Solar Energy Rejected	63%
Total Solar Energy Reflected	29%
Total Solar Energy Absorbed	46%
Total Solar Energy Transmitted	25%
Visible Light Transmitted	30%
Visible Light Reflected	20%
Ultra Violet Light Rejected	99%
Shading Coefficient	0.43
Glare Reduction	66%

Mechanical Properties

Thickness	250 micron	Peel Strength	7 lb/inch
Tensile Strength at Break	28,500 psi	Ply	2
Break Strength	260 lb/inch		
Elongation at Break	125%		

Performance Guide

Solar Heat Rejection	★★★★☆
Glare Reduction	★★★☆☆
UV Reduction	★★★★★
Fade Reduction	★★★★☆
Safety & Security	★★★★★
One-Way Privacy	☆☆☆☆☆
Two-Way Privacy	☆☆☆☆☆
Scratch Coating	Yes
Warranty Period	12 Years

Key: Excellent - ★★★★★ Some Benefit - ★★★☆☆ N/A - ☆☆☆☆☆