

SILVER 50

Performance Data

| | |
|----------------------------------|------|
| Total Solar Energy Rejected | 55% |
| Solar Energy Reflected | 29% |
| Solar Energy Absorbed | 38% |
| Solar Energy Transmitted | 33% |
| Visible Light Transmitted | 46% |
| Visible Light Reflected | 27% |
| Ultra Violet Light Rejected | 95% |
| Shading Coefficient | 0.50 |
| Solar Heat Gain Coeff. (g Value) | 0.44 |
| Emissivity | 0.74 |
| Glare Reduction | 48% |

Performance Guide

| | |
|----------------------|-----------|
| Solar Heat Rejection | ★ ★ ★ ☆ ☆ |
| Glare Reduction | ★ ☆ ☆ ☆ ☆ |
| UV Reduction | ★ ★ ★ ★ ★ |
| Fade Reduction | ★ ★ ★ ☆ ☆ |
| Safety & Security | ☆ ☆ ☆ ☆ ☆ |
| One-Way Privacy | ☆ ☆ ☆ ☆ ☆ |
| Two-Way Privacy | ☆ ☆ ☆ ☆ ☆ |
| Scratch Coating | Yes |
| Warranty Period | 12 Years |

Key: Excellent - ★★★★★ Some Benefit - ★☆☆☆☆ N/A - ☆☆☆☆☆

Film Notes

Very discreet with a slight blue tint when looked through from the inside. A good choice for fade reduction without sacrificing light and vision.

Please refer to your supplier for explanations on performance data, performance guide and application restrictions.