

# SOLAR BRONZE 35

## Performance Data

Total Solar Energy Rejected	65%
Solar Energy Reflected	36%
Solar Energy Absorbed	39%
Solar Energy Transmitted	25%
Visible Light Transmitted	35%
Visible Light Reflected	26%
Ultra Violet Light Rejected	97%
Shading Coefficient	0.39
Solar Heat Gain Coeff. (g Value)	0.34
Emissivity	0.69
Glare Reduction	60%

## Performance Guide

Solar Heat Rejection	★★★★☆
Glare Reduction	★★★☆☆
UV Reduction	★★★★★
Fade Reduction	★★★★☆
Safety & Security	☆☆☆☆☆
One-Way Privacy	★★☆☆☆
Two-Way Privacy	☆☆☆☆☆
Scratch Coating	Yes
Warranty Period	12 Years

Key: Excellent - ★★★★★ Some Benefit - ★☆☆☆☆ N/A - ☆☆☆☆☆

## Film Notes

Very good heat reduction and an ideal choice for performance with good light transmission.

*Please refer to your supplier for explanations on performance data, performance guide and application restrictions.*