

OPTITUNE 55

Performance Data

Total Solar Energy Rejected	39%
Total Solar Energy Reflected	12%
Total Solar Energy Absorbed	37%
Total Solar Energy Transmitted	51%
Visible Light Transmitted	58%
Visible Light Reflected	11%
Ultra Violet Light Rejected	99%
Shading Coefficient	0.71
Solar Heat Gain Coeff. (g Value)	0.61
Winter U Value	1.06
Emissivity	0.87
Glare Reduction	33%

Performance Guide

Solar Heat Rejection	★ ★ ★ ☆ ☆
Glare Reduction	★ ☆ ☆ ☆ ☆
UV Reduction	★ ★ ★ ★ ★
Fade Reduction	★ ★ ★ ☆ ☆
Safety & Security	☆ ☆ ☆ ☆ ☆
One-Way Privacy	☆ ☆ ☆ ☆ ☆
Two-Way Privacy	☆ ☆ ☆ ☆ ☆
Scratch Coating	Yes
Warranty Period	12 Years

Key: Excellent - ★★★★★ Some Benefit - ★☆☆☆☆ N/A - ☆☆☆☆☆

Film Notes

Very Light Neutral Film with some heat glare. OptiTune 'Dual Reflective' films provide reduced internal reflection. Ideal for residential use.

Please refer to your supplier for explanations on performance data, performance guide and application restrictions.