

# ARGENT 65

## Performance Data

Total Solar Energy Rejected	51%
Total Solar Energy Reflected	35%
Total Solar Energy Absorbed	21%
Total Solar Energy Transmitted	44%
Visible Light Transmitted	65%
Visible Light Reflected	26%
Ultra Violet Light Rejected	99%
Shading Coefficient	0.57
Solar Heat Gain Coeff. (g Value)	0.49
Winter U Value	0.96
Emissivity	0.69
Glare Reduction	28%

## Performance Guide

Solar Heat Rejection	★ ★ ★ ★ ☆
Glare Reduction	★ ☆ ☆ ☆ ☆
UV Reduction	★ ★ ★ ★ ★
Fade Reduction	★ ★ ★ ☆ ☆
Safety & Security	☆ ☆ ☆ ☆ ☆
One-Way Privacy	☆ ☆ ☆ ☆ ☆
Two-Way Privacy	☆ ☆ ☆ ☆ ☆
Scratch Coating	Yes
Warranty Period	7 Years

Key: Excellent - ★★★★★ Some Benefit - ★☆☆☆☆ N/A - ☆☆☆☆☆

## Film Notes

High quality, sputtered Argent 65 film with effective heat rejection whilst maintaining a good natural light level. Perfect for residential and shop front projects. Creates a subtle 'natural', very pale gold appearance. Requires a neutral silicone edge sealant.

*Please refer to your supplier for explanations on performance data, performance guide and application restrictions.*