


OptiTune 05

OPTICAL & SOLAR PROPERTIES

	Single Pane	Double Pane
Visible Light Transmitted	6 %	6 %
Visible Light Reflected (Int)	15 %	15 %
Visible Light Reflected (Ext)	63 %	63 %
Ultra Violet Block	99 %	99 %
Total Solar Energy Reflected	56 %	50 %
Total Solar Energy Transmitted	6 %	6 %
Total Solar Energy Absorbed	38 %	44 %
Emissivity (Room Side)	0.75	0.75
Glare Reduction	93 %	93 %
Shading Coefficient	0.19	0.31
Solar Heat Gain Coeff. (G-Value)	0.16	0.27
U-Value Winter (IP)	0.99	0.47
U-Value Winter (SI)	5.62	2.66
Luminous Efficacy	0.32	0.19
Total Solar Energy Rejected	84 %	73 %

R070R0W - OptiTune 05 Water Activated Adhesive



Ed-C DS No 1158 August 2011