


Silver 20 Low-E

OPTICAL & SOLAR PROPERTIES

	Single Pane	Double Pane
Visible Light Transmitted	17 %	16 %
Visible Light Reflected (Int)	63 %	63 %
Visible Light Reflected (Ext)	56 %	57 %
Ultra Violet Block	99 %	99 %
Total Solar Energy Reflected	51 %	46 %
Total Solar Energy Transmitted	12 %	11 %
Total Solar Energy Absorbed	37 %	43 %
Emissivity (Room Side)	0.39	0.39
Glare Reduction	81 %	81 %
Shading Coefficient	0.24	0.34
Solar Heat Gain Coeff. (G-Value)	0.20	0.29
U-Value Winter (IP)	0.79	0.41
U-Value Winter (SI)	4.49	2.31
Luminous Efficacy	0.71	0.47
Total Solar Energy Rejected	80 %	71 %

R06922E - Silver 20 Low E Pressure Sensitive Adhesive



Ed -A, D5 No, August 2011