


Silver Matte 20

OPTICAL & SOLAR PROPERTIES

	Single Pane	Double Pane
Visible Light Transmitted	19 %	18 %
Visible Light Reflected (Int)		
Visible Light Reflected (Ext)	56 %	56 %
Ultra Violet Block	99 %	99 %
Total Solar Energy Reflected	56 %	45 %
Total Solar Energy Transmitted	14 %	13 %
Total Solar Energy Absorbed	30 %	42 %
Emissivity (Room Side)	0.73	0.73
Glare Reduction	79 %	78 %
Shading Coefficient	0.28	0.38
Solar Heat Gain Coeff. (G-Value)	0.24	0.33
U-Value Winter (IP)	0.97	0.46
U-Value Winter (SI)	5.54	2.63
Luminous Efficacy	0.67	0.47
Total Solar Energy Rejected	76 %	67 %

R06920 - Silver Matte 20 Pressure Sensitive Adhesive



Ed-F DS No 1181 August 2011