


Silver Matte 20 Xtra

OPTICAL & SOLAR PROPERTIES

	Single Pane	Double Pane
Visible Light Transmitted	13 %	12 %
Visible Light Reflected (Int)	48 %	48 %
Visible Light Reflected (Ext)	60 %	60 %
Ultra Violet Block	99 %	99 %
Total Solar Energy Reflected	62 %	61 %
Total Solar Energy Transmitted	10 %	9 %
Total Solar Energy Absorbed	28 %	30 %
Emissivity (Room Side)	0.84	0.84
Glare Reduction	84 %	85 %
Shading Coefficient	0.22	0.16
Solar Heat Gain Coeff. (G-Value)	0.19	0.14
U-Value Winter (IP)	1.04	0.48
U-Value Winter (SI)	5.91	2.73
Luminous Efficacy	0.72	0.78
Total Solar Energy Rejected	81 %	86 %

R108SMX - Silver Matter 20 Xtra Pressure Sensitive Adhesive



Ed-A DS No 1447 August 2011