


# Silver 20

## OPTICAL & SOLAR PROPERTIES

	Single Pane	Double Pane
Visible Light Transmitted	18 %	17 %
Visible Light Reflected (Int)	62 %	62 %
Visible Light Reflected (Ext)	61 %	61 %
Ultra Violet Block	99 %	99 %
Total Solar Energy Reflected	55 %	49 %
Total Solar Energy Transmitted	13 %	12 %
Total Solar Energy Absorbed	32 %	38 %
Emissivity (Room Side)	0.71	0.71
Glare Reduction	80 %	79 %
Shading Coefficient	0.25	0.35
Solar Heat Gain Coeff. (G-Value)	0.22	0.30
U-Value Winter (IP)	0.97	0.46
U-Value Winter (SI)	5.51	2.62
Luminous Efficacy	0.72	0.49
Total Solar Energy Rejected	78 %	70 %

R06922W - Silver 20 Water Activated Adhesive  
 R05822S - Silver 20 Pressure Sensitive Adhesive



Ed-C DS No.1190 August 2011