CH 8 Exterior Window Film

Technical Specifications

Total Solar Energy:

Transmitted % 53.0
Reflected %..... 6.0
Absorbed % 41.0

Visible Light:

Transmitted % 8.0
Reflected Exterior % 4.0
Reflected Interior %..... 5.0
Glare Reduction % 91.0

Solar Heat Gain Coefficient..... 0.65
Shading Coefficient 0.75
Luminous Efficacy..... 0.11
Total Solar Energy Rejection %..... 35.0
Infrared Rejection %* 19.0

U Factor..... 1.03
Emissivity..... 0.85
Ultraviolet Rejection % ..... Exceeds 99.0

Read in accordance with National Fenestration Rating Council (NFRC) standards on 3mm clear glass.

* IR Rejection based on average transmission from 780-2500nm.

Warranty

Vertical:	Horizontal/Sloped:
3 Years	N/A

All external films requires edge sealing; use sealing agent Dow Corning 795 or 791, Max 5000 bg GE or equivelant neutral approved silicone seal agent for external application.

Please note: There may be restrictions concerning the suitability of this product to certain glazing types. If you would like general advice, please contact your supplier.

CH 8 Exterior is a non-reflective, exterior-applied film that significantly reduces glare and provides a uniform look to glass on commercial buildings.

Product Benefits

- Reduces Heat Gain
- Increases Privacy
- Lowers Energy Costs
- Rejects up to 99% of UV Rays
- Improves Shatter Resistance
- Significantly Reduces Glare
- Slows Fading of Fabrics, Flooring

This window film is an elegant, practical solution for comfort, protection and natural appearance. Enjoy your view by embracing sunlight while minimizing the negative effects of the sun such as glare, harmful ultraviolet exposure and unwanted heat.backed by a manufacturer's warranty.

Specification Use Statement

Reported values are typical properties and should not be used as a specification. Since the user is aware of the specific conditions in which the product is to be used, it is the user's responsibility to determine whether the product is suitable for intended use. If you need verification regarding specific use or additional information, please contact your supplier.